

## South African Chromite sand Specification

Item	Standard Content (%)	
Chromium Oxide/CrO	> 45	
Silica	<2	
Ferric Oxide/Fe <sub>2</sub> O <sub>3</sub>	<20	
Moisture Content	<0.1	
Calcium Oxide/CaO	<0.5	
Aluminium oxide/Al <sub>2</sub> O <sub>3</sub>	<22	
Magnesium oxide/MgO	<15	
Mesh	40-140 <30%	
Melting Point (°C)	1850	

